POLYMER PROPERTIES

Polymer Properties

- Polymer Properties Depend on Temperature and Time
 POLYMERS ARE VISCOELASTIC MATERIALS
 BOTH ELASTIC AND VISCOUS BEHAVIOR
- Polymer Properties and related Temperature Dependence Depend on the Physical State of the Polymer
 - Amorphous States
 - Melt State Hot cooked spaghettis no water
 - Glassy State Frozen cooked spaghettis
 - Solution State Hot cooked spaghettis in water
 - Partially Ordered Semicrystalline State: Mixture of Cooked and Raw spaghettis

AMORPHOUS STATE

Chain Conformation in the Amorphous State



A polymer chain in the amorphous state is described as a RANDOM COIL

The more flexible the chain, the more compact the coil (for a given number of repeat units).

Viscoelastic Behavior :

Strong Temperature and Time Dependence of Properties



When is a Polymer Amorphous?

Glassy Polymer

Amorphous below T_g: PS, PMMA, Epoxy at Room Temperature

Rubbery Polymer

Amorphous above T_g: Crosslinked High Molar Mass Polyisoprene, Polychloroprene, Silicones, Polybutadiene at room temperature

• Molten Semicrystalline Polymer Crystallizable Polymer above T_m : PE (T > 140°C), it-PP (T > 170°C), PET (T > 270°C), PEEK (T > 360°C)

• Between Crystals in Semicrystalline Polymers (T < T_m)

Why is a Polymer Amorphous ?

- Amorphous state stable above Tm
- Some polymers do not crystallize Why ?
 - Crystallization kinetics too slow (next chapter)
 - Structure is not conducive to order
 - · Tacticity defects
 - Regio defects
 - Branching (copolymerization)

Degree of Crystallinity of Statistical Ethylene Copolymers as a Function of Branch Content



Figure 3. Normalized degree of crystallinity at -20 °C after cooling from the mult for ethylene/1-octane, ethylene/1-bexane, ethylene/1-pentene, and ethylene/1-butene copolymers. The normalized degree of crystallinity is obtained by dividing the actual degree of crystallinity by the weight fraction of ethylene sequences along the polymer backbone.

Macromolecules, 1999

Properties of Amorphous Polymers

- Below T_g Molecular motion is very localized (vibrations and few bond rotations) Hard, Brittle and High Modulus
- In the T_g Region
 Onset of large-scale molecular motions (vibration and significant bond rotations)
 Soft, tough and lower Modulus.
 Properties depend on time/speed/frequency of perturbation
- Rubbery Plateau Region
- Flow Region

CRYSTALLINE STATE

Chain Conformations in the Crystalline State



FIGURE 6.2. A 3, their formed by a poly a-olefin, in this case polypropylene. This structure is also seen to fit a triangular template.



FIGURE 6.3. A poly molefin in the syndictactic configuration showing the rugs exquerce storng the chain, and the two fold belix which for a square template.

Helical Conformations

-(CH₂-CF₂)_n-

Poly(tetrafluoroethylene) PTFE



Figure 6-9 Molecular conformation of polytetrafluoroethylene: top-repeat unit of one molecule; bottom-carbon skeleton showing 13/6 helis. (Clark and Muus [27].)

Semicrystalline State: Spherulite



Poly(butylene sebacate) thin film observed with polarized light in an optical microscope.

- Polymer Crystals:
 - Similar to small molecules/metallic crystals
 - Three dimensional positional order
 - First-order transition
 - Different from small molecules/metallic crystals
 - Degree of crystallinity (T < T_m) is less than 100%
 - Unit cell never contains the whole chain
 - · Bonding differs greatly in different directions

- Crystallization Only Between T_g and T_m: Why ?
- Semicrystalline State: Properties depend on T !!
 - Hard and Rigid: $T < T_g < T_m$ Modulus is independent of the degree of crystallinity
 - Flexible: $T_g < T < T_m$ Modulus increases with the degree of crystallinity
- Degree of Crystallinity is controlled by:
 - Structure of polymer chain (defects, comonomers, etc..)
 - Thermal history: How so ?
- Kinetics of Crystallization

Polymer Crystal Melting Point Techniques for its Detection

- Simple Visual Observation: Contrast solid and liquid phases
 - Flow behavior (solid vs liquid, viscosity, cross-linking, T_g)
 - Light scattering (haze, index of refraction fluctuations)
- Quantitative Evaluation:
 - X-ray Diffraction: [Bragg peaks vs Amorphous Halo]
 - Birefringence: [crystal phase: n Ⅱ chain axis, n⊥ chain axis]
 - Calorimetry: $C_p(T) [C_p^{liq}(T), C_p^{sol}(T), H_{liq} H_{sol} = \Delta H_f \text{ at } T_m]$
 - Dilatometry: V(T), $[\alpha_{liq}, \alpha_{sol}, V_{liq}-V_{sol} = \Delta V_f \text{ at } T_m]$
 - Infrared Spectroscopy: [Bond vibration, Conformers]
 - Raman Spectroscopy: [Bond vibration, Conformers]

Morphology of Semicrystalline Polymers: Factors Controlling the Degree of Crystallinity

 Crystallization Conditions (thermal history): the higher the crystallization temperature, the higher the degree of crystallinity at the end of the primary crystallization stage (impingement).

2) Chain Structure: Increasing the molar mass Increasing tacticity defects Increasing comonomer content Lead to a decrease in crystallinity Increasing regio defects Increasing chain stiffness l_c : lamellar thickness l_a: amorphous layer thickness L : long spacing local crystallinity = l_c / L

Crystal Structure

- Type of Information:
 - Unit Cell Type and Dimensions
 - Conformations of Polymer Chains and 3D Packing
- Techniques:
 - X-Ray Diffraction and Electron Diffraction
 - IR and Raman Spectroscopy, Atomic Force Microscopy
- Problems:
 - Case Study: Compare diffraction pattern from a large NaCl crystal and from a sample of polyethylene.....

Definition of Rubber Elasticity and Requirements

- Definition of Rubber Elasticity: Very large deformability with complete recoverability.
- Molecular Requirements:
 - Material must consist of polymer chains.
 Need to change conformation and extension under stress.
 - Polymer chains must be highly flexible.
 Need to access conformational changes (not w/ glassy, crystalline, stiff mat.)
 - Polymer chains must be joined in a network structure.
 Need to avoid irreversible chain slippage (permanent strain).
 One out of 100 monomers must connect two different chains.
 Connections (covalent bond, crystallite, glassy domain in block copolymer)

Cross-links, Networks and Classes of Elastomers

- Chemical Cross-linking Process: Sol-Gel or Percolation Transition
- Gel Characteristics:
 - Infinite Viscosity
 - Non-zero Modulus
 - One giant Molecule
 - Solid Polymer Network



- Step Polymerization (isocyanates, oxirane)
- Chain Polymerization (styrene with divinylbenzene)
- Post-polymerization Reactions (vulcanization with sulfur)
- Cross-linked and Gels in the Food/Health Care Industry: Globular protein example: the egg white ! (S₂ bridges) Jello®, contact lenses, liquid soaps, shampoos (proteins, polysaccharides)

Polymer stress-strain behavior



Deformation of semicrystalline polymers

- Mechanism of elastic deformation
- Mechanism of plastic deformation
- Stress-strain curve relation



Tensile response brittle & plastic



RESEARCH METHODS IN POLYMER CHEMISTRY

A variety of lab techniques are used to determine the properties of polymers:

- Techniques such as wide angle X-ray scattering (WAXS), small angle X-ray scattering (SAXS) and small angle neutron scattering are used to determine the crystalline structure of polymers.
- Gel permeation chromatography is used to determine the number average molecular weight, weight average molecular weight, and polydispersity.
- Infrared or IR-spectroscopy is used to gather information about compound's structure, to assess its purity, and sometimes to identify it.
- Fourier transform infrared spectroscopy (FTIR), Raman spectroscopy and nuclear magnetic resonance (NMR) can be used to determine composition.

- Thermal properties such as the glass transition temperature and melting point can be determined by differential scanning calorimetry and dynamic mechanical analysis.
- **Pyrolysis** followed by analysis of the fragments is one more technique for determining the possible structure of the polymer.
- The scanning electron microscopy (SEM) is especially useful for routine examination of plastics, elastomers and biopolymers.
- There are many instruments that test the mechanical and viscoelastic properties of polymer materials. These instruments apply varied shear stress and shear rate to polymer samples to estimate their response to deformation and mechanical strength.
- Thermogravimetric analysis, or TGA, is commonly employed in research and testing to determine degradation temperatures, absorbed moisture content of materials, the level of inorganic and organic components in materials, decomposition points of explosives, and solvent residues.

Viscosity of Fluids η

- Viscosity: physical property characterizing the resistance of fluids to flow.
- Newton's Law of Viscosity
 Consider a fluid contained between two large plates of area A, separated by a
 small distance Y. We examine what happens when the lower plate initially at
 rest is set in motion at time t = 0 with a constant velocity V. As time proceeds
 the fluid gains momentum and after some time exhibits a steady-state velocity
 profile. When this state is reached, a constant force F is necessary to maintain
 the velocity of the lower plate at its initial value V.



Newton's Law of Viscosity



fluid of lesser y

Velocity of lower plate relative to upper plate

Distance over which the velocity is decreasing in the direction perpendicular to flow

> Local Velocity Gradient: Velocity in x-direction Gradient in y-direction

Polymers are Non-Newtonian Fluids



Figure 11.10 Schematic plot of shear stress versus strain rate for Newtonian and non-Newtonian fluids.

Polymer melts and solutions generally exhibit shear thinning: Can you think of one very important application, where this is very useful ?